



Apex Pro America, LLC

Tape. Film. Overlamination.

#9225

25 micron Unsupported Clear OPP Film (1 side treated)

Backing Biaxially Oriented Polypropylene

Corona treat

One side Corona treated

| | | Unit | Data | Test Method |
|-----------------------------------|-----------|---------|--------------|--------------------|
| Total Thickness | | micron | 25 + - 1 | ASTM D 2673 |
| Thickness Tolerance | | % | ± 4.0 | ASTM D 2673 |
| Tensile Strength | MD | Mpa | ≥140 | ASTM D 882 |
| | TD | | ≥250 | |
| Elongation | MD | % | ≤200 | ASTM D 882 |
| | TD | | ≤65 | |
| Heat Shrinkage | MD | % | ≤4.5 | ASTM D 1204 |
| | TD | | ≤3.5 | |
| Friction Coefficient (C.O.F.(Ud)) | | | ≤0.5 | ASTM D 1894 |
| Haze | | % | ≤2.0 | ASTM D 1003 |
| Gloss (45°) | | % | ≥85 | ASTM D 2457 |
| Corona Treated on one side | (outside) | dyne/cm | ≥35 | ASTM D 2578 |
| | (Inside) | | ≥38 | |

High transparency and glossy; Excellent oxygen and oil barrier performance; Abrasion resistance, Low property and high stifiness; good for printing, high speed sealable processing

Important Notice:

The above properties are approximate and should only provide references and be considered typical only. The accuracy and completeness are not guaranteed. User shall determine suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The seller limits its obligation to replacement or at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.